



Elgiloy Specialty Metals Hampshire Mill

Alloy 316Ti Stainless Steel

UNS: S31635
EN-DIN: 1.4571

Type 316Ti is a titanium stabilized version of Type 316 molybdenum-bearing austenitic stainless steel. The Type 316 alloys are more resistant to general corrosion and pitting/crevice corrosion than the conventional chromium-nickel austenitic stainless steels such as Type 304. They also offer higher creep, stress-rupture and tensile strength at elevated temperature. Type 316 stainless steel can be susceptible to sensitization – the formation of grain boundary chromium carbides at temperatures between approximately 900 and 1500 °F (425 to 815 °C) – which can result in rapid corrosion. Resistance to sensitization is achieved in Type 316Ti with titanium additions to stabilize the structure against chromium carbide precipitation, which is the source of sensitization. This stabilization is achieved by an intermediate temperature heat treatment, during which the titanium reacts with carbon to form titanium carbides. This significantly reduces susceptibility to sensitization in service by limiting the formation of chromium carbides. Thus, the alloy can be used for extended periods at elevated temperatures without compromising its corrosion resistance.

Nominal Composition

	C	Mn	P	S	Si	Cr	Ni	Mo	Ti	N	Fe
min	-	-	-	-	-	16.0	10.0	2.00	5X(C+N)	-	-
max	.080	2.0	0.045	0.030	0.75	18.0	14.0	3.00	0.70	0.10	BAL

Physical Properties

	At 70°F	At 20°C
Density	0.29 lb./in ³	7.99 g/cm ³
Modulus of Elasticity (E)	28.0 x 10 ³ ksi in tension	193 x 10 ³ MPa in tension
Coefficient of Expansion	9.2 x 10 ⁻⁶ microinches/in.-°F (32-212°F)	16.5 μm/m-°C (0-100°C)
Electrical Resistivity	28.4 μ ohm.in	72 μ ohm.cm
Thermal Conductivity	8.4 Btu-in./ft. ² hr.-°F (100°C)	14.6 W/m-K (100°C)

Applicable Specifications

ASME SA-240, ASTM A240

Typical Mechanical Properties – Typical Room Temperature Mechanical Properties

Condition	Tensile Strength (UTS)	0.2% YS	Elongation% in 2" (50.8 mm)	Hardness Rockwell
Annealed	90 ksi (620 MPa)	36 ksi (248 MPa)	54	76 HRBW

Typical mechanical properties are based on ATI source, ASTM A240

For further information email:
hampinfo@elgiloy.com or
call: (847) 453-0500

Elgiloy Specialty Metals
Hampshire Mill
One Hawk Road
Hampshire, IL 60140 USA

www.esmhampshire.com

The information and data in this product data sheet are accurate to the best of our knowledge and belief, but are intended for general information only. Applications suggested for the materials are described only to help readers make their own evaluations and decisions, and are neither guarantees nor to be construed as express or implied warranties of suitability for these or other applications. Data was obtained from our melt sources with data referring to mechanical properties and chemical analyses are the result of tests performed on specimens obtained from specific locations with prescribed sampling procedures; any warranty thereof is limited to the values obtained at such locations and by such procedures. There is no warranty with respect to values of the materials at other locations. Further information should be sought from the melt sources.