



Elgiloy Specialty Metals Hampshire Mill

Alloy 347 Stainless Steel

UNS: S34700
EN-DIN: 1.4550

347 alloys are stabilized stainless steels which offer as their main advantage an excellent resistance to intergranular corrosion following exposure to temperatures in the chromium carbide precipitation range from 800 to 1500°F (427 to 816°C). 347 alloys are stabilized by the addition of columbium.

Nominal Composition

	C	Mn	P	S	Si	Cr	Ni	Nb (Cb)	N	Fe
min	-	-	-	-	-	17.0	9.0	10xC	-	-
max	.08	2.0	0.045	0.030	1.00	19.0	12.0	1.00	0.10	BAL

Physical Properties

	At 70°F	At 20°C
Density	0.288 lb./in ³	7.96 g/cm ³
Modulus of Elasticity (E)	28.0 x 10 ³ ksi	193 x 10 ³ MPa
Coefficient of Expansion	9.2 x 10 ⁻⁶ microinches/in.-°F (70-600°F)	16.6 μm/m-°C (20-300°C)
Electrical Resistivity	28.4 μ ohm.in	72 μ ohm.cm
Thermal Conductivity	9.5 Btu-in./ft. ² hr.-°F	16.3 W/m-K

Applicable Specifications

AMS 5512, ASTM A269, ASTM A240, ASTM A479, AMS 5680

Typical Mechanical Properties – Typical Room Temperature Mechanical Properties

Condition	Tensile Strength (UTS)	0.2% YS	Elongation% in 2" (50.8 mm)	Hardness Rockwell
Annealed	93 ksi (640 MPa)	37 ksi (250 MPa)	45	84 HRBW

Typical mechanical properties are based on ATI source, ASTM A240

For further information email:
hampinfo@elgiloy.com or
call: (847) 453-0500

Elgiloy Specialty Metals
Hampshire Mill
One Hawk Road
Hampshire, IL 60140 USA

www.esmhampshire.com

The information and data in this product data sheet are accurate to the best of our knowledge and belief, but are intended for general information only. Applications suggested for the materials are described only to help readers make their own evaluations and decisions, and are neither guarantees nor to be construed as express or implied warranties of suitability for these or other applications. Data was obtained from our melt sources with data referring to mechanical properties and chemical analyses are the result of tests performed on specimens obtained from specific locations with prescribed sampling procedures; any warranty thereof is limited to the values obtained at such locations and by such procedures. There is no warranty with respect to values of the materials at other locations. Further information should be sought from the melt sources.